

# ARTHROPLASTY

Micromotion at the tibial plateau in primary and revision total knee arthroplasty: fixed *versus* rotating platform designs

## **Objectives**

Initial stability of tibial trays is crucial for long-term success of total knee arthroplasty (TKA) in both primary and revision settings. Rotating platform (RP) designs reduce torque transfer at the tibiofemoral interface. We asked if this reduced torque transfer in RP designs resulted in subsequently reduced micromotion at the cemented fixation interface between the prosthesis component and the adjacent bone.

Composite tibias were implanted with fixed and RP primary and revision tibial trays and

biomechanically tested under up to 2.5 kN of axial compression and 10° of external femoral

component rotation. Relative micromotion between the implanted tibial tray and the neighbouring bone was quantified using high-precision digital image correlation techniques.

Rotational malalignment between femoral and tibial components generated 40% less overall tibial tray micromotion in RP designs than in standard fixed bearing tibial trays. RP

#### Methods

**Results** 

JRSI Foundation, Inc., Indiana, United States

S. R. Small, MS, Engineering Director
R. A. Malinzak, MD, Orthopaedic Surgeon
M. A. Ritter, MD, Executive Director
JRSI Foundation, Inc., 1199 Hadley Road, Mooresville, IN 46158, USA.

 R. D. Rogge, PhD, Professor of Biology and Biomedical Engineering
 E. M. Reyes, PhD, Assistant Professor of Mathematics
 P. L. Cook, MS, Undergraduate student
 K. A. Farley, BS, Undergraduate student
 Rose-Hulman Institute of Technology, 5500 Wabash Avenue, Terre Haute, IN 47803, USA.

Correspondence should be sent to Mr S. R. Small; email: smallsr@ rose-hulman.edu

doi:10.1302/2046-3758.54.2000481

Bone Joint Res 2016;5:122–129. Received: 24 June 2015; Accepted: 29 February 2016

# trays reduced micromotion by up to 172 $\mu$ m in axial compression and 84 $\mu$ m in rotational malalignment models.

## Conclusions

Reduced torque transfer at the tibiofemoral interface in RP tibial trays reduces relative component micromotion and may aid long-term stability in cases of revision TKA or poor bone quality.

Cite this article: Bone Joint Res 2016;5:122–129.

Keywords: micromotion; total knee arthroplasty; rotating platform; biomechanics; initial stability

## **Article focus**

- An investigation of tibial component stability as it relates to femoral and tibial component malalignment in total knee arthroplasty (TKA).
- Establishment of a methodology to assess movement at the bone-implant interface using three-dimensional digital image correlation.

#### **Key messages**

Rotating platform tibial components generate reduced implant micromotion by lessening tibiofemoral torque transfer.

#### **Strengths and limitations**

- The study is the first to implement noncontact digital image correlation methodologies to quantify three-dimensional micromotion between the tibial tray and neighbouring bone in a TKA model.
- This study is limited in that it uses composite tibial specimens in a simplified loading scenario in order to assess difference in stability of fixed and rotating platform component designs.

# Introduction

Cemented total knee arthroplasty (TKA) has been a highly successful elective procedure,



S. R. Small,

R. D. Rogge,

E. M. Reyes,

K. A. Farley, M. A. Ritter

P. L. Cook,

R. A. Malinzak,

BIR

with excellent long-term survivorship in several different device designs.<sup>1-9</sup> Polyethylene wear resulting in osteolysis and aseptic loosening is a common, multifactorial, late-term failure mechanism in cemented arthroplasty. Micromotion at the cement-implant and cement-bone interfaces may contribute to this failure mechanism through predisposition to focal osteolysis and the enabling of polyethylene wear debris to migrate into the bone distally.<sup>10,11</sup> Because adequate initial stability of cemented TKA tibial prostheses contributes to long-term success of the implant, several prior studies focused on increased stability through cementing technique and surface preparation.<sup>11-16</sup> Fewer studies have investigated the role of device design in improving implant stability in cemented tibial trays.

Tibial component micromotion is a mechanical result of the combination of shear forces and moments at the tibiofemoral joint generated during the complex biomechanics at the knee during gait. Mobile-bearing tibial components were introduced in the late 1970s in order to decouple the shear moments generated by rotation between femoral and tibial components during knee flexion.<sup>17</sup> These designs enable high articular conformity and decreased polyethylene contact stress, reducing articular wear in addition to reducing post damage in constrained condylar and posterior stabilised designs.<sup>18-22</sup> Previous studies have documented reduced torque transfer from femoral component rotation and malalignment at the tibiofemoral articulation with mobile bearing designs, subsequently reducing torsion-induced strain across the proximal tibia.<sup>23,24</sup> The reduction of torsion-induced strain during knee loading following mobile-bearing TKA may decrease excessive loading at the bone-cement and cement-prosthesis interface, thus reducing the rate of interface fatigue.

Understanding the mechanical implications of rotation at the knee as a result of flexion or rotational malalignment is crucial for maximising component stability and promoting durable implant-cement-bone interfaces, particularly during revision TKA. Prior studies have described reduced torque transfer and cortical tibial strain in tibias implanted with rotating platform (RP) mobile-bearing tray designs.<sup>23,24</sup> We therefore asked if the RP TKA designs result in improved tibial tray stability and decreased component micromotion in both the primary and revision settings.

## **Materials and Methods**

In this study, relative micromotion was measured within tibial specimens implanted with one of four prosthesis designs: fixed-bearing, posterior stabilised primary components (PFC Sigma, DePuy Orthopaedics Inc., Warsaw, Indiana); RP, posterior stabilised primary components (PFC Sigma, DePuy Orthopaedics, Inc.); fixed-bearing, posterior stabilised revision components with 115 mm × 14 mm press-fit distal stem and reduced intercondylar width (PFC TC3, DePuy Orthopaedics Inc.); and RP, posterior stabilised revision components with 75 mm × 14 mm press-fit distal stem and reduced intercondylar width (PFC TC3, DePuy Orthopaedics Inc.). All tibial trays were manufacturer 'Size 3' with 10 mm thick polyethylene bearings. Fourth generation composite tibial specimens (Medium, Left, Model 3401, Pacific Research Laboratories, Vashon, Washington) were chosen as the test specimen for their reduced interspecimen variability as compared with cadaveric tissue.<sup>25,26</sup> All tibial components were implanted by a board certified orthopaedic surgeon (RAM) using standard instrumentation and high-viscosity polymethylmethacrylate (PMMC) bone cement (SmartSet HV, DePuy Orthopaedics Inc.) following the manufacturer's suggested surgical technique of 0° of posterior slope and surgeon preference of neutral varus-valgus alignment based on the long axis of the composite tibia.

Primary tibial components were fully cemented along the baseplate and stem, while revision components utilised press-fit fixation in the distal stem, with proximal cementing limited to the underside of the tibial tray. Cement was finger-packed to both the component and tibial plateau and manually impacted. Full tibial tray seating was attained in all specimens and visually verified by the implanting surgeon. A total of six tibial specimens were implanted per experimental group.

Biomechanical testing was conducted on a biaxial electrodynamic materials testing machine (ElectroPuls E10,000 A/T, Instron, Norwood, Massachusetts). Specimens were incorporated into the materials testing machine via a custom fixture allowing free medial/lateral and anterior/ posterior translation of the potted base. Femoral components selected to match tibial component size and design (PFC Sigma and PFC T3 Size 3, DePuy Orthopaedics, Inc.), were integrated into the upper testing grips to allow for repeatable load application through the femoral component onto the polyethylene bearing surface at the lowest preferred dwell point. A silicon-based lubricant (DM-Fluid-350CS, Shin-Etsu Chemical Co, Tokyo, Japan) was applied between all articulating surfaces to lubricate the otherwise dry in vitro test environment. Testing was conducted in two phases: compressive loading ramped at a rate of 60 N/s to a peak load of 2.5 kN, followed by femoral component rotation at a rate of 0.5 degrees per second to a final position of 10° external tibiofemoral malalignment. In all instances the femoral component was positioned in 90° of flexion. A total of five trials were repeated for each of four digital image correlation (DIC) viewing angles (anterior, medial, posterior, and lateral) in all 24 specimens, with micromotion data collected as the change in position of each data point between the start and completion of each testing phase.

DIC was used in this study to provide non-contact micromotion analysis with greater precision than alternative techniques, namely linear variable displacement transducers (LVDTs). A set of two calibrated, high



A finely distributed black and white speckle pattern applied to the tibia cortex and the outer rim of the tibial tray. (Right) Three dimensional surface mapping via digital image correlation software allowing spatial tracking of bone and metal reference points.

resolution cameras with 50 mm lenses (5M, GOM Inc., Braunschweig, Germany) were used in conjunction with the ARAMIS 5.0 software suite (GOM Inc.) to perform DIC displacement analysis through surface pattern matching across a series of images during testing. The paired cameras were fixed on a single tripod at a 20° angle relative to each other, 400 mm apart and at a distance of 1 m from the test specimen. In preparation for optical pattern matching analysis, a thin basecoat of white paint was applied to the proximal tibial cortex and the peripheral rim of the tibial tray. A fine black speckle pattern was then painted over the primed surface to generate a pattern tuned to the specifications of the DIC system manufacturer template (Fig. 1). A post hoc speckle analysis using a custom MATLAB program (Mathworks, Inc., Natick, Massachusetts) showed a mean speckle size of 0.04 mm<sup>2</sup>. During each loading sequence (no load, compression only, compression with rotation) image data was collected in a 160 mm × 135 mm × 120 mm calibrated 3D field of view. Because DIC is a line-of-sight measurement technique, trials were repeated in each anterior, medial, posterior and lateral view in order to capture data at all regions of interest around the periphery of the proximal tibia and tibial tray. Following testing, measurement points on the tibial tray were paired with partner points within close proximity to the tray on the proximal tibial cortex in each of the anterior, medial, lateral, posteromedial and posterolateral measurement regions. To calculate micromotion, a line was drawn between each corresponding pair of measurement points within the DIC software package. The 3D change in length of this line over time was tracked throughout the loading cycle via ARAMIS 5.0 digital image correlation software (GOM, Inc.). Coordinate data of the line was exported from the digital image correlation software package and analysed in a custom programmed MATLAB algorithm (MATLAB R2010b, Mathworks, Inc.).

To address the repeated measurements taken on the bone specimens, generalised estimating equations (GEE) were used to estimate a marginal linear model for the mean micromotion; a separate model was considered for the axial and torsional tests. For each model, a compound symmetric structure was specified for the working correlation matrix. The primary analysis considered the effects of the component design, bearing mobility, and measurement region. The effect of the component design was allowed to depend on the bearing mobility. A secondary analysis was conducted to make comparisons of individual measurement regions. The primary models above were altered to allow the effects of design and the bearing mobility to depend on the measurement region, creating a fully saturated model. All pairwise comparisons were then estimated. All analyses were conducted in R version 3.2.2 (2015-08-14). The generalised estimating equations were fit using the geepack package (version 1.2.0).

## Results

Micromotion analysis was conducted in two stages of joint loading: axial compression and rotational malalignment. Tibial component micromotion generated as a result of axial compression is presented in Figure 2 with statistical comparisons between device designs presented in Tables I and II. Across all bones and measurement regions, the average repeatability within each bone and measurement region subset of data was 74 µm in axial testing. From this data there is no evidence that the overall axial compression micromotion is dependent upon the primary versus revision component design (p = 0.845), however, the model suggests that, on average, the axial compression micromotion is somewhat related to bearing mobility (p = 0.055) and is strongly associated with the measurement region (p < 0.001). A statistically significant difference between fixed and RP



Mean relative micromotion between implanted tibial tray and the composite tibia specimen as a result of 2.5 kN axial compression. The estimated mean micromotion and associated 95% confidence intervals (CI) are included. Symbols are used to link measurements associated with the same bone within the group of interest. (F, Fixed; RP, rotating platform).

Table I. Co	omparisons of mean	micromotion (µm	, (95% confidence	e interval)), res	ponse in axial (	compression: fix	xed <i>vs</i> mobile
-------------	--------------------	-----------------	-------------------	-------------------	------------------	------------------	----------------------

	Region	Fixed	RP	p-value
Primary	Anterior	110 (69 to 179)	80 (47 to 113)	0.259
•	Medial	174 (119 to 229)	108 (76 to 140)	0.042
	Posteromedial	271 (216 to 326)	204 (174 to 234)	0.035
	Posterolateral	235 (182 to 288)	231 (185 to 277)	0.927
	Lateral	260 (243 to 277)	215 (154 to 276)	0.165
Revision	Anterior	106 (54 to 158)	74 (14 to 134)	0.423
	Medial	153 (117 to 192)	126 (88 to 164)	0.344
	Posteromedial	186 (117 to 255)	201 (134 to 268)	0.760
	Posterolateral	221 (168 to 274)	214 (168 to 260)	0.834
	Lateral	340 (251 to 429)	168 (133 to 203)	< 0.001

p-value from pairwise comparison

RP, rotating platform

tibial component designs was observed in two measurement regions in the primary component design, with the fixed bearing primary tray exhibiting significantly higher micromotion in the medial (+ 66 µm, p = 0.042) and posteromedial (+ 67 µm, p = 0.035) measurement regions. Likewise, a 172 µm (p < 0.001) greater micromotion was observed in the lateral measurement region of the fixed bearing components when comparing bearing mobility within the revision component design.

Tibial component micromotion generated as a result of rotational malalignment between the tibial and femoral components is presented in Figure 3 with statistical comparisons presented in Tables III and IV. Across all bones and measurement regions, the average repeatability within each bone and measurement region subset of data was 41 µm in rotational malalignment testing. The rotational malalignment model suggests tibial tray micromotion is dependent upon primary *versus* revision component design (p = 0.001), bearing mobility (p < 0.001), and the measurement region (p < 0.001). Furthermore, there is evidence that the effect of the component design is dependent upon the bearing mobility (p = 0.018). Specifically, for fixed bearing devices, the micromotion for revised components tends to be 42 µm greater than that for primary components. However, for RP devices, the micromotion for revision components tents to be only 9 µm greater than that for primary components. So, the RP design appears to dampen the impact of moving from a primary to a revision component design. Under torsional loading as a result of rotational malalignment, the fixed bearing primary tray exhibited significantly higher micromotion than the primary RP tray in the medial (+62  $\mu$ m, p < 0.001) and lateral regions  $(+10 \,\mu\text{m}, p = 0.013)$ . Rotational malalignment in the revision tibial trays resulted in higher micromotion in the fixed bearing trays at the anterior (+84  $\mu$ m, p < 0.001), Table II. Comparisons of mean micromotion (µm, (95% confidence interval)), response in axial compression: primary vs revision.

	Region	Primary	Revision	p-value
Fixed	Anterior	110 (69 to 179)	106 (54 to 158)	0.907
	Medial	174 (119 to 229)	153 (117 to 192)	0.542
	Posteromedial	271 (216 to 326)	186 (117 to 255)	0.060
	Posterolateral	235 (182 to 288)	221 (168 to 274)	0.732
	Lateral	260 (243 to 277)	340 (251 to 429)	0.080
RP	Anterior	80 (47 to 113)	74 (14 to 134)	0.862
	Medial	108 (76 to 140)	126 (88 to 164)	0.469
	Posteromedial	204 (174 to 234)	201 (134 to 268)	0.947
	Posterolateral	231 (185 to 277)	214 (168 to 260)	0.601
	Lateral	215 (154 to 276)	168 (133 to 203)	0.189

p-value from pairwise comparison



Mean relative micromotion between implanted tibial tray and the composite tibia specimen as a result of 10° femoral component rotation. The estimated mean micromotion and associated 95% confidence intervals are included. Symbols are used to link measurements associated with the same bone within the group of interest. (F, Fixed; RP, rotating platform).

medial (+82 µm, p < 0.001), posterolateral (+59 µm, p < 0.001) and lateral (+45 µm, p < 0.001) measurement regions. When directly comparing rotation-induced micromotion between primary and revision tibial trays, the revision fixed bearing tray exhibited 78 µm (p < 0.001) and 42 µm (p < 0.001) higher micromotion than the primary fixed bearing tray in the posterolateral and lateral regions, respectively. The revision RP tray exhibited 18 µm (p = 0.033) higher micromotion than the primary RP tray in the medial measurement region.

## Discussion

The vastly different mechanics of RP and fixed bearing tibial trays are a result of the manufacturers' aim to decouple motion and constraint at the tibiofemoral interface. RP designs result in decreased torque transfer through the prosthesis at the joint articulation and decreased torsional strain response in the proximal tibia as a result of tibiofemoral rotation during gait or due to component malrotation. While component micromotion is most commonly studied in cementless applications, component stability is critical for long-term clinical success in cemented TKA as well. Therefore, this study was designed to compare the relative stability of cemented, fixed and RP tibial tray designs in both the primary and the more highly constrained revision scenario.

Rotational malalignment between the femoral and tibial components in TKA of over 10° has been described in up to 12% of TKA cases,<sup>27</sup> and has been clinically associated with persistent pain and early revision.<sup>28-31</sup> Previous studies have observed torsional loads between 8.2 Nm to 16.9 Nm as a result of 10° of malrotation in fixed bearing tray designs with a reduction of 68% to 91% reduction in torque in mobile-bearing versions of the tibial tray<sup>23,24,32</sup> The current study demonstrated a significant reduction in component micromotion as a result of the reduced torque transfer in the RP designs. Micromotion as a result of interface torque due to rotational malalignment in

Table III. Comparisons of mean micromotion (µm, (95% confidence interval)) response in rotational malalignment: fixed vs mobile.

	Region	Fixed	RP	p-value	
Primary	Anterior	65 (7 to 123)	13 (9 to 17)	0.078	
	Medial	81 (54 to 108)	19 (8 to 30)	< 0.001	
	Posteromedial	59 (36 to 82]	71 (53 to 89)	0.401	
	Posterolateral	64 (45 to 83)	75 (66 to 84)	0.301	
	Lateral	25 (15 to 35)	15 (7 to 23)	0.013	
Revision	Anterior	99 (64 to 134)	15 (6 to 24)	< 0.001	
	Medial	119 (78 to 160)	37 (21 to 53)	< 0.001	
	Posteromedial	67 (31 to 103)	82 (54 to 110)	0.519	
	Posterolateral	142 (123 to 161)	83 (64 to 102)	< 0.001	
	Lateral	67 (31 to 103)	22 (17 to 27)	< 0.001	

p-value from pairwise comparison

RP, rotating platform

Table IV. Comparisons of mean micromotion (µm (95% confidence intervals) response in rotational malalignment: primary vs revision.

	Region	Primary	Revision	p-value	
Fixed	Anterior	65 (7 to 123)	99 (64 to 134)	0.335	
	Medial	81 (54 to 108)	119 (78 to 160)	0.134	
	Posteromedial	59 (36 to 82)	67 (31 to 103)	0.705	
	Posterolateral	64 (45 to 83)	142 (123 to 161)	< 0.001	
	Lateral	25 (15 to 35)	67 (31 to 103)	< 0.001	
RP	Anterior	13 (9 to 17)	15 (6 to 24)	0.678	
	Medial	19 (8 to 30)	37 (21 to 53)	0.065	
	Posteromedial	71 (53 to 89)	82 (54 to 110)	0.519	
	Posterolateral	75 (66 to 84)	83 (64 to 102)	0.464	
	Lateral	15 (7 to 23)	22 (17 to 27)	0.145	

p-value from pairwise comparison

RP, rotating platform

fixed bearing TKA designs were a mean of 79 microns (25 to 142) across all measurement regions, compared with a mean of 43 microns (13 to 83) across all measurement regions in RP designs. Overall an average 40% reduction in torque-induced component micromotion was observed with the RP designs. Additionally, the RP design exhibited reduced micromotion when compared with the fixed bearing designs during the direct axial compression phase of the loading cycle in two primary and one revision measurement region. This difference in compressive stability was unexpected and perhaps reflects some unrecognised bias in the methodology.

Micromotion has historically been measured in biomechanical models as a means to quantify stability of an implant in both cemented and cementless orthopaedic applications. Prior studies have utilised fixed and intrusive electromechanical transducers for single-axis measurement or computational methods for estimated micromotion analysis.33-39 The introduction of digital image correlation technologies into biomechanical research has allowed for non-contact optical measurement of the relative displacement between implant and bone in three dimensions with high accuracy and resolution for increased measurement ease and expanded research applications. For example, in a recent study, Mann et al<sup>40</sup> used DIC to assess micromotion in tibial components in postmortem retrieval specimens and reported a measurement error of 1.1 µm using similar point-to-point techniques as the current study. Additionally, we established a measurement uncertainty of 3.4  $\mu$ m of the system and methodology used in the current study during micromotion analysis in a total hip arthroplasty model.<sup>41</sup> That uncertainty measurement was made by comparing point-to-point change in displacement between a fixed and translated baseplate across an 8 mm gage length as measured by both DIC and linear variable displacement transducer (LVDT) methods.<sup>41</sup>

Because rigid initial fixation is essential for proper bone ingrowth and long-term survivorship in porous coated devices, most TKA biomechanical micromotion studies have focused on the assessment of uncemented tibial trays. Far fewer studies have focused on the stability and micromotion in cemented components as the degree of micromotion is less critical in the short-term following cemented TKA. Nevertheless, the use of PMMC bone cement remains the current standard in TKA fixation, and as such, adequate fixation of the tibial baseplate and minimisation of interface fatigue is essential for the reduced risk of aseptic loosening in the large population of cemented-TKA patients.

Micromotion analysis of the cemented TKA has been used to compare the inherent stability of cementation techniques.<sup>33-35</sup> In a cadaveric biomechanical study, Peters et al<sup>33</sup> measured tibial tray micromotion to compare full *versus* surface cementation in cruciate and I-beam stem designs. In four measurement regions around the tibial plateau, Peters et al<sup>33</sup> reported linear micromotion ranging between 2 microns and 20 microns in a liftoff model and found no difference in stability between cementing techniques. Conversely, Luring et al<sup>34</sup> observed increased liftoff micromotion, ranging from 3 microns to 29 microns, with hybrid fixation in comparison with a fully cemented tibial tray in a composite tibia model. In an early study, Sala, Taylor and Tanner<sup>35</sup> compared initial torsional stability in press-fit, press-fit with supplemental screw fixation, and horizontally cemented tibial trays in a cadaveric model. In that study, reduced micromotion was observed with cemented fixation, most notably during phases of high torque and low axial load, and in specimens with poor bone quality. In good quality bone, mean torsioninduced micromotion ranged from 25 microns to 73 microns in press-fit trays, 24 microns to 49 microns in trays with supplemental screw fixation, and 21 microns to 35 microns in cemented trays. However, in poor quality bone, micromotion exceeded 350 microns in the press-fit trays and exceeded 150 microns in the cemented tray. In the current study, we observed significantly different stability characteristics between RP and fixed bearing tibial trays in both the primary and revision settings. Higher torsioninduced micromotion (20 microns to 141 microns) and compression-induced micromotion (72 microns to 331 microns) are likely the result of higher testing loads, as well as the comparison of three-dimensional micromotion as measured by DIC as compared with linear micromotion as measured by physical electromechanical transducers.

The authors acknowledge limitations in the methodology of this study which may affect the clinical extrapolation of the data. While manufactured tibia specimens have been validated to exhibit similar material properties to cadaveric tissue, with decreased interspecimen variability, these bone models are a broad simplification of the natural physiological system: lacking soft tissue interactions, bony remodeling, and natural kinematics. Composite specimens were chosen in order to minimise specimen variability in the experimental set-up and ensure prosthesis design as the single primary variable of interest. Additionally, a simplified loading pattern was used in testing which does not fully represent the complex biomechanics produced during gait. Recent studies have shown that greatest micromotion in TKA is observed during periods of low axial load, whereas in this study a full axial load of 2.5 kN was used during micromotion measurement.35-37 This loading profile is artificial and may not reflect the actual in vivo performance of the knee, but was chosen in this study as it allows for the relative comparison of micromotion between the device designs in a controlled manner. The significant differences observed between fixed and RP devices in this loading scenario would perhaps be amplified with lower axial loads. While most knee function occurs at much less femoral flexion, a femoral component position of 90° flexion was chosen as this setup resulted in the highest induced torque in a prior analysis of this design,<sup>24</sup> and because this is the range of flexion wherein the femoral component begins interaction with the tibial post. In the current study the primary tibial trays were fully cemented, while revision systems were proximally cemented with press-fit stems. Primary stability in TKA is inherently sensitive to cementation procedure, thus alterations in the cementing and press-fit techniques in these components will invariably change the micromotion response of the trays under physiological loading. Additionally, the relatively small sample size in each experimental group limits the statistical methodology available for establishing the distribution of the data. Furthermore, there was no robust method established to determine the effect of repeated tests required to capture line-of-sight measurements at the five different regions of interest. Ideally, simultaneous data capture from multiple cameras used in stereo would eliminate the need for repeated tests in order to capture data from all measurement points.

In conclusion, relative dynamic stability of the implanted tibial tray in TKA is substantially influenced by tibial tray design. Considerable micromotion as a result of knee joint torque was observed in fixed bearing designs and in more highly constrained revision prostheses. Decoupling of joint torgue at the tibial tray through a RP bearing affords increased implant stability as a result of relative tibiofemoral rotation either through gait or due to suboptimal component alignment. The results of this study demonstrate, in a benchtop model, the significant reduction of component micromotion within the RP tray design. Despite this theoretical advantage of tray design, no difference in long-term performance has been established in the literature between fixed and mobile-bearing designs.<sup>42</sup> Concerns remain regarding the potential of backside wear associated with the introduction of an additional bearing surface in mobile-bearing trays. Because of this, further work is needed to evaluate the clinical efficacy of the mobile-bearing TKA, particularly in scenarios of poor bone stock and revision arthroplasty, in which micromotion and interface fatigue in cemented designs may play a greater role in long-term survivorship.

#### **Supplementary material**

Figures showing experimental set up and micromotion measurement regions are available alongside the online version of this article at www.bjr .boneandjoint.org.uk

#### References

- Kim YH, Kim JS, Choe JW, Kim HJ. Long-term comparison of fixed-bearing and mobile-bearing total knee replacements in patients younger than fifty-one years of age with osteoarthritis. *J Bone Joint Surg [Am]* 2012;94-A:866-873.
- Kim YH, Yoon SH, Kim JS. The long-term results of simultaneous fixed-bearing and mobile-bearing total knee replacements performed in the same patient. J Bone Joint Surg [Br] 2007;89-B:1317-1323.
- Callaghan JJ, Wells CW, Liu SS, Goetz DD, Johnston RC. Cemented rotatingplatform total knee replacement: a concise follow-up, at a minimum of twenty years, of a previous report. J Bone Joint Surg [Am] 2010;92-A:1635-1639.

- 4. Ritter MA. The Anatomic Graduated Component Total Knee Replacement: A Long-Term Evaluation with 20-year Survival Analysis. J Bone Joint Surg. 2009;91-B:745-749.
- 5. Rodriguez JA, Bhende H, Ranawat CS. Total condylar knee replacement: a 20-year followup study. Clin Orthop Relat Res 2001;388:10-17.
- 6. Vessely MB, Whaley AL, Harmsen WS, Schleck WSCD, Berry D. J. Longterm Survivorship and Failure Modes of 1000 Cemented Condylar Total Knee Arthroplasties. Clin Orthop Relat Res 2006;452:28-34.
- 7. Carothers JT, Kim RH, Dennis DA, Southworth C. Mobile-bearing total knee arthroplasty: a meta-analysis. J Arthroplasty 2011;26:537-542.
- 8. Hopley CDJ, Crossett LS, Chen AF. Long-term clinical outcomes and survivorship after total knee arthroplasty using a rotating platform knee prosthesis: a metaanalysis. J Arthroplasty 2013;28:68-77.e1, 3.
- 9. Tarkin IS, Bridgeman JT, Jardon OM, Garvin KL. Successful biologic fixation with mobile-bearing total knee arthroplasty. J Arthroplasty 2005;20:481-486.
- 10. Jacobs JJ, Shanbhag A, Glant TT, Black J, Galante JO. Wear Debris in Total Joint Replacements. J Am Acad Orthop Surg 1994;2:212-220.
- 11. Vanlommel J, Luyckx JP Jr, Labey L, et al. Cemented the Tibial Component in Total Knee Arthroplasty. J Arthroplasty 2011;26:492-496.
- 12. Schlegel UJ, Siewe J, Delank KS, et al. Pulsed lavage improves fixation strength of cemented tibial components. Int Orthop 2011;35:1165-1169.
- 13. Schlegel UJ, Püschel K, Morlock MM, Nagel K. An in vitro comparison of tibial tray cementation using gun pressurization or pulsed lavage. Int Orthop 2014;38:967-971.
- 14. Miskovsky C, Whiteside LA, White SE. The cemented unicondylar knee arthroplasty. An in vitro comparison of three cement techniques. Clin Orthop Relat Res 1992:284:215-220
- 15. Bert JM, McShane M. Is it necessary to cement the tibial stem in cemented total knee arthroplasty? Clin Orthop Relat Res 1998;356:73-78.
- 16. Walker PS, Soudry M, Ewald FC, McVickar H. Control of cement penetration in total knee arthroplasty. Clin Orthop Relat Res 1984;185:155-164.
- 17. Callaghan JJ, Squire MW, Goetz DD, Sullivan PM, Johnston RC. Cemented Rotating-Platform Total Knee Replacement. J Bone Joint Surg [Am] 2000;82-A:705-711.
- 18. Fisher J, McEwen H, Tipper J, Galvin AL, Ingram J, Kamali A, Stone MH, Ingham E. Wear, Debris, and Biologic Activity of Cross-linked Polyethylene in the Knee: Benefits and Potential Concerns. Clin Orthop Relat Res 2004;428:114-119.
- 19. Fisher J, McEwen H, Tipper J, Galvin AL, Ingram J, Kamali A, Stone MH, Ingham E. Wear-simulation Analysis of Rotating-platform Mobile-Bearing Knees. Orthopedics 2006;29(9 Suppl):S36-41.
- 20. Goldstein WM, Gordon AC, Swope S, Branson J. Rotating Platform Revision Total Knee Arthroplasty. J Knee Sura 2012; 25(1):45-50.
- 21. Currier JH, Mayor MB, Collier JP, Currier BH, Van Critters DW. Wear Rate in a Series of Retrieved RP Knee Bearings. Journal of ASTM International 2011;8(3):10.
- 22. Puloski SK, McCalden RW, MacDonald SJ, Rorabeck CH, Bourne RB. Tibial Post Wear in Posterior-Stabilized Total Knee Arthroplasty: An Unrecognized Source of Polyethylene Debris. J Bone Joint Surg [Am] 2001;83-A:390-397.
- 23. Bottlang M, Erne OK, Lacatusu E, Sommers MB, Kessler O. A mobile-bearing knee prosthesis can reduce strain at the proximal tibia. Clin Orthop Relat Res 2006;447:105-111.
- 24. Malinzak RA, Small SR, Rogge RD, et al. The effect of rotating platform TKA on strain distribution and torque transmission on the proximal tibia. J Arthroplasty 2014;29:541-547.
- 25. Cristofolini L, Viceconti M. Mechanical validation of whole bone composite tibia models. J Biomech 2000:33:279-288.
- 26. Heiner AD. Structural properties of fourth-generation composite femurs and tibias. J Biomech 2008;41:3282-3284.
- 27. Uehara K, Kadoya Y, Kobayashi A, Ohashi H, Yamano Y. Bone anatomy and rotational alignment in total knee arthroplasty. Clin Orthop Relat Res 2002;402: 196-201
- 28. Arima J, Whiteside LA, McCarthy DS, White SE. Femoral rotational alignment, based on the anteroposterior axis, in total knee arthroplasty in a valgus knee. A technical note. J Bone Joint Surg [Am] 1995;77-A:1331-1334.
- 29. Barrack RL, Schrader T, Bertot AJ, Wolfe MW, Myers L. Component rotation and anterior knee pain after total knee arthroplasty. Clin Orthop Relat Res 2001;392:46-55.
- 30. Berger RA, Crossett LS, Jacobs JJ, Rubash HE. Malrotation causing patellofemoral complications after total knee arthroplasty. Clin Orthop Relat Res 1998;356:144-153.

- 31. Anouchi YS, Whiteside LA, Kaiser AD, Milliano MT. The effects of axial rotational alignment of the femoral component on knee stability and patellar tracking in total knee arthroplasty demonstrated on autopsy specimens. Clin Orthop Relat Res 1993:287:170-177
- 32. Kessler O, Lacatusu E, Sommers MB, Mayr E, Bottlang M. Malrotation in total knee arthroplasty: effect on tibial cortex strain captured by laser-based strain acquisition. Clin Biomech 2006;21:603-609
- 33. Peters CL, Craig MA, Mohr RA, Bachus KN. Tibial component fixation with cement: full- versus surface-cementation techniques. Clin Orthop Relat Res 2003:409:158-168
- 34. Luring C, Perlick L, Trepte C, et al. Micromotion in cemented rotating platform total knee arthroplasty; cemented tibial stem versus hybrid fixation. Arch Orthop Trauma Surg 2006;126:45-48.
- 35. Sala M, Taylor M, Tanner KE. Torsional stability of primary total knee replacement tibial prostheses: a biomechanical study in cadaveric bone. J Arthroplasty 1999:14:610-615
- 36. Taylor M, Barrett DS, Deffenbaugh D. Influence of loading and activity on the primary stability of cementless tibial trays. J Orthop Res 2012;30:1362-1368.
- 37. Chong DYR, Hansen UN, Amis AA. Analysis of bone-prosthesis interface micromotion for cementless tibial prosthesis fixation and the influence of loading conditions ./ *Biomech* 2010:43:1074-1080
- 38. Bhimji S, Meneghini RM. Micromotion of cementless tibial baseplates under physiological loading conditions. J Arthroplasty 2012;27:648-654.
- 39. Bhimji S, Meneghini RM. Micromotion of cementless tibial baseplates: keels with adjuvant pegs offer more stability than pegs alone. J Arthroplasty 2014;29:1503-1506
- 40. Mann KA, Miller MA, Goodheart JR, Izant TH, Cleary RJ. Peri-implant bone strains and micro-motion following in vivo service: a postmortem retrieval study of 22 tibial components from total knee replacements. J Orthop Res 2014;32:355-361
- 41. Small SR, Hensley SE, Cook PL, Stevens RA, Rogge RD, Berend ME. The Effect of Stem Length on Strain and Micromotion in the Proximal Femur Following Total Hip Arthroplasty [abstract]. Proceedings to the Orthopaedic Research Society Annual Meeting, 2015.
- 42. Moskal JT, Capps SG. Rotating-platform TKA no different from fixed-bearing TKA regarding survivorship or performance: a meta-analysis. Clin Orthop Relat Res 2014:472:2185-2193.

#### Funding Statement

- Funding has been received from DePuy Synthes by the IRSI Foundation to offset study costs.
- Funding has also been received from the National Science Foundation (Grants #0923135 and #1039716) by Rose-Hulman Institute of Technology for the purchase of instrumentation used in this study.
- Malinzak reports funding received from Arthrex, Biomet and DePuy, none of which is related to this article.
- S. Small reports funding received from Biomet, DePuy, Exactech, Stryker and Orthalign, none of which is related to this article.
- M. Ritter reports funding received from Biomet, DePuy, Exactech and Stryker, none of which is related to this article.

#### Author Contribution

- S. R. Small: Study design, mechanical testing, manuscript preparation, revision, and final approval
- R. D. Rogge: Study design, Mechanical testing, Logistical oversight, Final approval.
- R. A. Malinzak: Specimen preparation, Clinical correlation, Final approval E. M. Reyes: Statistical analysis, manuscript preparation, and final approval.
- P. L. Cook: Mechanical testing, Data collection, Final approval.
- K. A. Farley: Mechanical testing, Data collection, Final approval. M. A. Ritter: Logistical oversight, Clinical correlation, Manuscript review, Final approval.

#### ICMJE conflict of interest

K. Farley reports that "While I was an undergraduate at the time of this study, I am now a product development engineering in the shoulder/extremities department of DePuy Orthopaedics.

© 2016 Small et al. This is an open-access article distributed under the terms of the Creative Commons Attributions licence (CC-BY-NC), which permits unrestricted use, distribution, and reproduction in any medium, but not for commercial gain, provided the original author and source are credited.

# Micromotion at the tibial plateau in total knee arthroplasty

# #425 MAY 2019 1.5 CE CREDITS \$

- In this study, relative micromotion was measured within tibial specimens with one of four prosthesis designs. Which of the following was NOT one of them?
- **a.** Fixed-bearing, posterior stabilized primary components
- **b.** Fixed-bearing, posterior stabilized revision components
- c. Fixed-bearing, rotating platform (RP)
- d. RP, posterior stabilized revision components
- True or False: All tibial components were implanted using high-viscosity PMMC bone cement.
- a. True
- **b.** False
- 3. How many trials were repeated for each of the four digital viewing angles?
- **a.** Four
- **b.** Five
- **c.** Six
- d. Seven

# 4. How was micromotion calculated?

- Generalized estimating equations were created.
- **b.** Visual inspections occurred on each view.
- c. An analysis was conducted to measure the regions.
- **d.** A line was drawn between each measuring points.
- 5. Micromotion analysis was conducted in how many stages of joint loading?
- **a.** 2
- **b.** 3
- **c.** 4 **d.** 5
- **u.** כ
- True or False. A water-based lubricant was applied between all articulating surfaces to combat the conditions during the test environment.
- **a.** True
- **b.** False
- 7. Mobile-bearing tibial components were introduced in the \_\_\_\_\_.
- **a.** 1950s
- **b.** 1960s
- **c.** 1970s
- **d.** 1980s

- 8. Which designs resulted in decreased torque transfer through the prosthesis at the joint articulation?
- a. Fixed
- b. RP
- c. Both of the above
- **d.** Neither of the above
- 9. True or False. The RP design exhibited reduced micromotion when compared with the fixed bearing designs during the direct axial compression phase of the loading cycle in two primary and one revision measurement region.
- a. True
- **b.** False

10. Understanding the mechanical implications of rotation of the \_\_\_\_\_ is crucial for maximizing component stability.

- a. Tibial spine
- **b.** Tibia
- c. Tibial plateau
- **d.** Knee

# MICROMOTION AT THE TIBIAL PLATEAU IN TOTAL KNEE ARTHROPLASTY #425

NBSTSA Certification No.		
AST Member No.		
□ My address has changed. The addre	ess below is the new a	ddress.
Name		
Address		
City	State	Zip
Telephone		
Check enclosed  Check Numb	er	
If you want to mail in your CEs, but still 800-637-7433.	want to pay by credit (	card, give us at call at

а	b	C	d

MAY 2019

1

2

3

5

8

g

10

# 1.5 CE CREDITS \$9

# Make It Easy - Take CE Exams Online

You must have a credit card to purchase test online. We accept Visa, MasterCard and American Express. Your credit card will only be charged once you pass the test and then your credits will be automatically recorded to your account.

Log on to your account on the AST homepage to take advantage of this benefit.



# Earn CE Credits at Home

You will be awarded continuing education (CE) credits toward your recertification after reading the designated article and completing the test with a score of 70% or better. If you do not pass the test, it will be returned along with your payment.

Send the original answer sheet from the journal and make a copy for your records. If possible use a credit card (debit or credit) for payment. It is a faster option for processing of credits and offers more flexibility for correct payment. When submitting multiple tests, you do not need to submit a separate check for each journal test. You may submit multiple journal tests with one check or money order.

# Members this test is also available online

at *www.ast.org.* No stamps or checks and it posts to your record automatically!

# Members: \$6 per credit (per credit not per test) Nonmembers: \$10 per credit

(per credit not per test plus the \$400 nonmember fee per submission)

After your credits are processed, AST will send you a letter acknowledging the number of credits that were accepted. Members can also check your CE credit status online with your login information at *www.ast.org.* 

# **3 WAYS TO SUBMIT YOUR CE CREDITS**

Mail to: AST, Member Services, 6 West Dry Creek Circle Ste 200, Littleton, C0 80120-8031

Fax CE credits to: 303-694-9169

E-mail scanned CE credits in PDF format to: memserv@ast.org

For questions please contact Member Services *memserv@ast.org* or 800-637-7433, option 3. Business hours: Mon-Fri, 8:00a.m. - 4:30 p.m., MT

# WRITE FOR US!

We are always looking for CE authors and surgical procedures that haven't been written about or the latest advancements on a commonplace surgery. You don't have to be a writer to contribute to the Journal. We'll help you every step of the way, AND you'll earn CE credits by writing a CE article that gets published! Here are some guidelines to kick start your way on becoming an author:



An article submitted for a CE must have a unique thesis or angle and be relevant to the surgical technology profession.



The article must have a clear message and be accurate, thorough and concise.

It must be in a format that maintains the Journal's integrity of style.

It must be an original topic (one that hasn't been published in the Journal recently.)

# How to Get Started

The process for writing a CE can be painless. We are here to assist you every step of the way and make sure that you are proud of your article.

- Write to *publications@ast.org*, and state your interest in writing, and what topic you would like to author.
- Submit an outline of your proposed topic for review. Once the outline is returned to you for approval, begin writing your manuscript. Getting your outline approved will save you time and effort of writing a manuscript that may be rejected.
- Submit your manuscript, as well as any art to illustrate your authored topic. You will be notified upon receipt of receiving the manuscript and as well as any changes, additions or concerns.

# Things to Remember:

- **Length:** Continuing education articles should run a minimum of 2,000 words and a maximum of 5,000 words.
- **References:** Every article concludes with a list of ALL references cited in the text. All articles that include facts, history, anatomy or other specific or scientific information must cite sources.
- **Copyright:** When in doubt about copyright, ask the AST editor for clarification.
- Author's Responsibility: All articles submitted for publication should be free from plagiarism, should properly document sources and should have attained written documentation of copyright release when necessary. AST may refuse to publish material that they believe is unauthorized use of copyrighted material or a manuscript without complete documentation.

Don't delay! Become an author today. Write to us at publications@ast.org